



Between the World
and The Weather
Since 1928

Poly-Felt 265VP

Polyester Reinforcement Fabric

(For Hot Elastomeric Built-up Roofing Applications)

DESCRIPTION

Barrett Poly-Felt 265VP reinforcement is specifically engineered for premium high performance roofing. It is a spun-bond polyester reinforcement fabric made with a continuous filament and needlepunched. The manufacturing process provides isotropic properties with excellent strength-to-weight ratio.

Most polyester reinforcements use low melting-point binders. Poly-Felt 265VP is bonded with a heat resistant, cross-linked acrylic binder, providing excellent thermal stability. It is uniquely suited for use with hot asphalt applications. A condensing process during manufacture provides optimum fiber distribution and mat thickness which enhances bitumen "bleed-through" saturation from both top and bottom during application. These characteristics create a completely monolithic waterproof membrane, with all levels of bitumen connected with fibrous reinforcement, forming a tough, homogeneous, multi-ply, redundant waterproofing assembly.

USES

- Ply Sheet for Ram-Tough Elastomeric Built-up Roofing
- Ply sheet for enhanced BUR systems
- Suitable for repair work on bituminous roofing systems
- Backer-sheet for composite base flashing systems

FEATURES

- Toughness and Strength - Four plies provides strain-energy that is more than 42 times greater than 4 ply fiber glass built-up membranes.
- Flexibility and thermo-conformability - can be "molded" to irregular substrates with hot asphalt.
- Fatigue Life - withstands daily expansion and contraction due to thermal cycling, better than rubber.
- Triple the puncture and tear resistant of fiberglass sheets.
- Durability - State-of-the-art polyester reinforcing, coupled with the unique waterproofing properties of Barrett's elastomeric roofing bitumens, offers a **"no compromise"** roofing assembly.

BENEFITS

- Versatility - Strength, flexibility, ease of application make Poly-Felt 265VP an ideal component for new construction, reroof, restoration and greenroof applications.
- Ease of Application - Poly-Felt 265 VP accommodates most substrates, angles, and curves, making applications faster and easier than more rigid fiberglass reinforcement products.
- Faster Installation - Lightweight rolls require less handling for more applied roofing. For each 10,000 sq.ft of 4 ply roofing, a fiberglass assembly requires 80 rolls, weighing 5,200 lbs.. Poly-Felt 265VP requires 40 rolls, weighing only 1600 lbs.,significantly reducing labor handling costs.

TYPICAL PHYSICAL PROPERTIES

| Test | Typical Values |
|------------------------|----------------|
| Basic Weight | 170 gm/m |
| Mat Weight, oz/sq.yd | 5.1 |
| Thickness, mils | 26 |
| Strip Tensile, lb/in | |
| MD | 73 |
| CD | 42 |
| Strip Elongation, % | |
| MD | 40 |
| CD | 35 |
| Shrinkage @ 392F. % | |
| MD | 0.9 |
| CD | -0.20 |
| Trap Tear Strength, lb | |
| MD | 33 |
| CD | 22 |
| Color | Black |

APPLICATION GUIDE

When using Poly-Felt in a built-up roof membrane assembly, all plies must be fully encapsulated in hot bitumen. In no place shall one ply of felt touch another. All felts are to be laid shingle fashion, overlapping the previous sheet 27 inches (12-1/2 inch exposure) for a 3 ply membrane and 30 inches (9-1/2 inch exposure) for a 4 ply membrane. End laps shall be minimum 6 inches and staggered a minimum of 18 inches between sheets.

When starting the Poly-Felt installation, apply the appropriate starter strips to achieve the proper ply count throughout the membrane installation.

To insure total adhesion, all felts shall be broomed or pressed into the bitumen while still hot.

PACKAGING

Roll Size - 39.75 in x 324 ft (1000 sq.ft.-approx. coverage)
 Roll Weight - 40 lbs. per roll
 Rolls per Pallet - 20
 Weight per Pallet - 800 lbs. (approx.)

APPLICATION PRECAUTIONS

- Do not apply to wet or damp surfaces
- Do not use materials that have become wet or damaged
- Cover material stored outside with a full cover breathable tarp
- Follow all recommended application guidelines
- **READ MATERIAL SAFETY DATA SHEET BEFORE USING**
- **FOR PROFESSIONAL ROOFING CONTRACTOR USE ONLY.**

PRODUCT SAFETY INFORMATION

Barrett Poly-Felt 265VP offers no unusual health or safety risks for a product of this nature. As with any roofing process, proper ventilation, clothing and eye protection is important.

For specific information, contact the Barrett Company for a current Material Safety Data Sheet on this product.

The user should not assume that all safety measures are indicated or that other measures may not be required.

Note

All statements, information and data given herein are believed to be accurate and reliable, but are presented without guaranty, warranty or responsibility of any kind, expressed or implied, except as may be indicated herein. Statements or suggestions concerning possible uses of our products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent.