

RamShield 250HTSA

Technical Data Sheet



TEST PROPERTIES	TEST STANDARD	TYPICAL VALUES
UNROLLABILITY	ASTM D1970	NO CRACKING, TEARING OR DAMAGE
THICKNESS MILS	ASTM D 5147	60 mils
TENSILE STRENGTH	ASTM D 1970	MD95/CD61
ADHESION TO PLYWOOD LB/FT	ASTM D 1970	-
40° F	-	9.5
75° F	-	46.8
THERMAL STABILITY	ASTM D 1970	260F /Pass
LOW TEMPERATURE FLEXIBILITY	ICC AC 48	PASS
TEAR RESISTANCE LB/F	ASTM D 1970	MD124/CD96
PERMEABILITY	ASTM E96	0.08
NAIL SEALABILITY	ASTM D 1970	PASS
TEMPERATURE RANGE	-	-40° F to 260° F
FIRE RATING	ASTM E 108	CLASS A
WATERPROOF INTEGRITY OF LAP SEAM	-	PASS
MAX LOAD,LBF/IN	ASTM D 1970	MD95/CD61

SPECIFICATIONS

LENGTH PER ROLL
WIDTH PER ROLL
WEIGHT PER ROLL
SQUARES PER ROLL
ROLLS PER PALLET
GR. WEIGHT PER PALLET

DATA

66.7'
36"
48 LBS
2
25
1250 lbs