

# Ram ColdTar® Plus

## Restoration Roof Coating



### Description

Ram ColdTar® Plus is a unique single-component thermoplastic rubber adhesive coating compound designed for existing roof applications. The combination of compounds, specifically to provide a monolithic, elastomeric membrane that's resistant to ponded water and other elements

### Uses

Ram ColdTar Plus can be used for the repair and resurfacing of existing asphalt, gravel surface built-up and coal tar based built-up roofs and modified bitumen sheet membrane systems. Ram ColdTar Plus is also appropriate for flat and sloped roofs and resists ponded water. Using the existing membrane as its base, the Ram ColdTar Plus, when cured, provides, a new durable waterproof surfacing.

### Coverage

Smooth Roof Surfaces Requiring a Reflective Coating  
Approximately = 3 gal/100 sq ft

Smooth Roof Surface Requiring a Granulated Surface  
Approximately = 3 gal/100 sq ft (max)

Granulated Surface Receiving a New Granulated Top  
Surface Approximately = 5 gal/100 sq ft

Granulated Roof surface Receiving a Reflective Topcoat  
Approximately = 4 gal/100 sq ft

### Properties

| Description                         | Measurement       | Test Method |
|-------------------------------------|-------------------|-------------|
| Water                               | 0.5% or less      | ASTM D-95   |
| Non-Volatile Content                | 62 - 64%          | ASTM D-6511 |
| Mineral and/or other stabilizers    | 3.79%             | ASTM D-4    |
| Uniformity/Workability              | Pass              | ASTM D-6511 |
| Pliability at 32°F                  | Pass              | ASTM 6511   |
| Viscosity                           | 10,000-15,000 cps | ASTM D-2196 |
| Density                             | 7.9 lbs/gal       | ASTM D-1475 |
| Tensile Strength                    | 190 psi (min.)    | ASTM D-412  |
| Elongation @ 77°F                   | >2000%            | ASTM D-412  |
| Elongation @ -40°F                  | 472%              | ASTM D-412  |
| Low Temperature flexibility @ -76°F | Pass              | ASTM D-5147 |

### Packaging

5 gallon pails  
45 lbs per pail  
36 pails per pallet

LIMITED WARRANTY: Barrett warrants its Products to be free of defects in materials, but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Barrett makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE, with respect to The Barrett Company, LLC. Barrett to replace or to refund the purchase price of the quantity of Barrett proven to be defective, and Barrett shall not be liable for any loss or damage.

20.1  
Document: KF-01012



800 | 647 | 0100  
F 908 | 647 | 0278