Ram 201

Modified Bitumen Light-Duty Protective Base



Product Description

Ram 201 is a polyester reinforced, SBS modified bitumen membrane with sanded surfaces. The high strength polyester reinforcement gives the composite membrane excellent tensile strength, toughness, puncture, and tear resistance creates a light-duty protection course.

Basic Uses

Ram 201 is used for a ligh duty for the protection course of RamTough 250, RamTough KLB-100 and Black Pearl.

Coverage

321 sq. ft. (27.87m²)

Properties

Test Results
Thickness 52 mils (1.3mm)

Tensile Max. Load (lbf/in) at 73.4± 3.6°F 116 MD/104XD 23°C± °C

Elongation at 0±3.6°F (%) 4.2 MD/4.0 XD

-15°F MD/XD Low Temperature Flex ° (max) 26.1°C MD/XD

Dimensional Stability % (max) <0.1 MD/XD

Compound Stability Temp (°) 215°F (101.67°C) Tear Strength at 73.4 \pm 3.6°F (lbf) 82MD/73XD (N) 365.7MD/325.58

Physical properties per ASTM D 6163 Type I, Grade S



Note All statements, information and data given herein are believed to be accurate and reliable, but are presented without guaranty, warranty or

accurate and reliable, but are presented without guaranty, warranty or responsibility of any kind, expressed or implied, except as may be indicated herein. Statements or suggestions concerning possible uses of our products are made without representation or warranty that any such use is free of patent infringement and are not recommended to infringe any patent.

Roll Width 36 in. (.91m)
Roll Length 107ft. (32.9m)
Roll Size 321 sq. ft. (29.8m²)
Roll Weight (per 100 sq. ft. 81.5 lbs. (37Kg)
Pallet Size 45" x 45" (1.143m x 1.143m)

LIMITED WARRANTY: Barrett warrants its Products to be free of defects in materials, but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Barrett makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE, with respect to The Barrett Company, LLC. Barrett to replace or to refund the purchase price of the quantity of Barrett proven to be defective, and Barrett shall not be liable for any loss or damage.

20.1

Document: KF-01017



800 | 647 | 0100 F 908 | 647 | 0278