

Ram 203

Modified Bitumen Medium-Duty Protection Course



Description

Ram 203 is a SBS polymer-modified, fiberglass reinforced asphalt membrane with sanded surfaces, top and bottom to create a medium-duty protection course.

Uses

Ram 203 can be used as a medium-duty protection course for RamTough 250 and RamTough KLB-100 applications.

Coverage

159 sq ft



Properties

Description	Measurement	Test Method
Thickness	2.2 mm/86 mils	
Reinforcement	Fiberglass	
Max. Load at 0±3.6°F (lbf/in)	91 (15.9 kN/m)	ASTM D-6163
Elongation at 0±3.6°F (%)	4.5	ASTM D-6163
Max. Load at 73.4±3.6°F (lbf/in)	41 (7.2 kN/m)	ASTM D-6163
Elongation at 73.4±3.6°F (%)	3.7	ASTM D-6163
Tear Strength at 73.4±3.6°F (lbf)	73 (12.8 kN/m)	ASTM D-6163
Low Temp. Flex 0°F Max.	-15 (26.1°C)	ASTM D-6163
Dimensional Stability (%) Max.	<0.1	ASTM D-6163
Compound Stability Temp (°F)	250 (121°C)	ASTM D-6163



Packaging

39"x49'
90 lbs. per roll
30 per pallet

LIMITED WARRANTY: Barrett warrants its Products to be free of defects in materials, but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Barrett makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE, with respect to The Barrett Company, LLC. Barrett to replace or to refund the purchase price of the quantity of Barrett proven to be defective, and Barrett shall not be liable for any loss or damage.

20.1
Document: KF-01017



800 | 647 | 0100
F 908 | 647 | 0278