# Liquid Flash 100

## High-Performance Single-Component Joint Sealant (100% Solids)



Colors

Black

Bronze

Stone

• Tan

Gray

White

Dark Bronze

Limestone

### Description

**Liquid Flash 100 (100% Solids)** is a high-performance interior/exterior joint sealant for use in both moving and non-moving joint applications. Liquid Flash 100 provides a long-lasting weathertight seal to a variety of building substrates.

\*\*Please use the correct product grade that complies with VOC regulations as per federal, state, county and city regulations/ codes at the place of installation of product.

### Features & Benefits

- 100% Solids = no Shrinkage
- · Applies Vertically & Overhead
- Bonds to Damp Masonry
- · Durable, Lasting Seal
- Easy to Trowel & Gun
- Excellent Weathering Properties
- · Fast Skinning Resists Dirt Pickup
- Gun Grade

**Properties** 

- Hybrid Substrate Bonding
- No Mixing or Priming
- No Solvents or Odor
- Non-Slump
- · Safe in Confined Spaces
- Single Component
- Unique Polymer
- Water Curable

# Uses

- Block and Masonry
- Curtain Walls
- Parapets
- Roofing Details
- Weather Sealing
- Cove Joints
- Expansion Joints
- Pre-Cast Concrete
- Siding
- Window & Door Frames

#### **Substrates**

- Aluminum
- Brick
- EPDM
- Galvanized Metal
- Metal
- SBS Mod Bitumen
- Vinyl

- Block
- Concrete
- Foam
- Masonry
  PVC
- • • •
- Stone
- Wood

Packaging

Cartridge (10.1 oz)

60 cases per pallet

Sausage (20 oz)

45 cases per pallet

24 cartridges per case

12 sausages per case

#### Description Measurement Test Method Specific Gravity $1.60 \pm 0.1$ Viscosity (Brookfield RVT, >1,000,000 cps TF Spindle, 4RPM, 73°F/23°C) Odor Mild Ester Smell Service Temp. (Continuous) -25°F to 200°F (-31.7°C to 93.3°C) Low Temp. Flex -10°F (-23.3°C) pas 1/4" Mandrel Slump (Sag) Zero Slump ASTM C697 Hardness 30 ± 3 (Shore A) ASTM D2240 Shear Strength 150 ± 15 psi (1.03 ± 0.1 mPa) **ASTM D1002** ASTM C679 Tack-Free Time 40 - 50 minutes 300 - 400% ASTM D412 Elongation Shrinkage (After 14 days) No Measurable Shrinkage Thermal Compatibility to Concrete Strong \*Compressive strength was checked on composite of silica sand (12 mesh, 6.5 Moh's minimum

\*Compressive strength was checked on composite of silica sand (12 mesh, 6.5 Moh's minimur hardness) and 18 to 20% of CR Sealant in a 4"x8" cylinder.

LIMITED WARRANTY: Barrett warrants its Products to be free of defects in materials, but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Barrett makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE, with respect to The Barrett Company, LLC. Barrett to replace or to refund the purchase price of the quantity of Barrett proven to be defective, and Barrett shall not be liable for any loss or damage.

20.1 Document: KF-01027



\_ \_\_\_\_

hing dor Spaces